

PAT-NO: JP409252931A
DOCUMENT-IDENTIFIER: JP 09252931 A
TITLE: CURTAIN FOR SHIELDING LIGHT
PUBN-DATE: September 30, 1997

INVENTOR-INFORMATION:
NAME
HAGIWARA, KOSHIRO
UCHIDA, TAKEHIKO

ASSIGNEE-INFORMATION:
NAME COUNTRY
HAGIWARA KOSHIRO N/A

APPL-NO: JP08063995

APPL-DATE: March 21, 1996

INT-CL (IPC): A47H023/08, A47H023/04 , C23C014/20

ABSTRACT:

PROBLEM TO BE SOLVED: To provide a light curtain excellent in a light shielding property, heat shielding property or the like without sacrificing the decorative property of cloth itself of the curtain by pinching a synthetic resin film formed with a metallic film between two cloths.

SOLUTION: A light shielding curtain has a biaxially stretched polyester film 3 formed with an aluminum evaporated film and pinched between resin made prints 1, 2, and hot melt adhesives 5, 6 having ethylene-vinyl acetate copolymer as the main component are applied to the surface of the film 3 for adhesion. Further, the clothe is selected from clothing fabrics like a drape, print and plain cloth. A method for forming a metallic film on the surface of

the
synthetic resin film is preferably a vacuum vaporization method from
an
economical point of view. Also, aluminum is preferable for the metal
of
metallic film from points of view of the operability, light shielding
property,
economy or the like. The thickness of the metallic film is selected
within
1-15 μ m of the extent so that the transmission factor of the
synthetic resin
film formed with the metallic film is less than 5%.

COPYRIGHT: (C)1997,JPO